

DECLARATION

I, Hironobu KAZUHARA, residing at Matsugasaki 219-8, Kashiwa-shi, Chiba-ken, Japan, do hereby declare that I am familiar with the English and Japanese languages and that the annexed document in the English language is a full and faithful translation, prepared by me, of the certified copy of the Japanese Patent Application No. 2002-269867 filed September 17, 2002.

Dated this 26th day of February, 2007

Hironobu KAZUHARA

PATENT OFFICE JAPANESE GOVERNMENT

This is to certify that the annexed is a true copy of the following application as filed with this Office.

Date of Application:

September 17, 2002

Application Number: Patent Application No. 2002-269867

Applicant:

YOKOGAWA ELECTRIC CORPORATION

Tadashi MATSUNAGA

June 2, 2003

Commissioner,

Shinichiro OOTA (Sealed)

Japan Patent Office

Shutusho No. Shutusho Patent 2003-3042697



[Name of Document]

Patent Application

[Case Number]

02A0137

[Addressee]

Commissioner of Patent Office

[International Classification]

C12Q 1/68

[Inventor]

[Address or Residence]

4-20-15 Hon-Cho, Koganei-shi Tokyo, Japan

[Name]Tadashi MATSUNAGA

[Address or Residence]

c/o Department of Biotechnology, Tokyo University of Agricultural & Technology

2-24-16, Naka-Cho, Koganei-shi, Tokyo, Japan

[Name]Haruko TAKEYAMA

[Inventor]

[Address or Residence]

c/o Department of Biotechnology, Tokyo University of Agricultural & Technology

2-24-16, Naka-Cho, Koganei-shi, Tokyo, Japan

[Name]Brandon YOZA

[Inventor]



[Address or Residence]

c/o YOKOGAWA ELECTRIC CORPORATION

9-32, Nakacho 2-chome, Musashino-shi, Tokyo 180-8750,

Japan

[Name]Kazuhisa FUKUSHIMA

[Address or Residence]

c/o YOKOGAWA ELECTRIC CORPORATION

9-32, Nakacho 2-chome, Musashino-shi, Tokyo 180-8750,

Japan

[Name]Saya SATOU

[Applicant for Patent]

[Code Number]

000006507

[Name]

YOKOGAWA ELECTRIC CORPORATION

[Representative]

ISAO Uchida

[Applicant for Patent]

[Address or Residence] 4-20-15 Hon-Cho, Koganei-shi Tokyo, Japan

[Representative]

Tadashi MATSUNAGA

[Indication of Charge]

[Prepayment Table Ledger Number] 005326

[Amount of Payment]

21,000 yen

[List of Filed Materials]

[Name of Material] Specification 1

[Name of Material] Drawing 1

[Name of Material] Abstract 1

[Confirmation of Proof] Proof Necessary



[NAME OF DOCUMENT]

[TITLE OF THE INVENTION]

METHOD OF EXTRACTING NUCLEIC ACID OR PROTEIN USING DENDRIMERS AND DENDRIMER-

COMPOSITIONAL SUBSTANCES

[CLAIMS]

[Claim 1]

A method of extracting nucleic acid or protein using dendrimers, in which multi-layer dendrimers are formed on the surface of fine particles, amino radicals are formed on the surface of the dendrimers, and nucleic acid or protein is extracted or recovered using these amino radicals.

[Claim 2]

A method of extracting nucleic acid or protein using dendrimers in accordance with claim 1, wherein said fine particles are those of bacteria-derived magnetic bodies, artificial magnetic bodies, metals, plastic beads, glass beads, or gel state substances.

[Claim 3]

A method of extracting nucleic acid or protein using dendrimers in accordance with claim 1 or claim 2, wherein said dendrimers are laminated on the surface of said fine particles after treating the surface of said fine particle with silane using a sililation reagent or a silane-coupling reagent.

[Claim 4]

A method of extracting nucleic acid or protein using dendrimers in accordance with any of claims 1 to 3, wherein said dendrimers are of the second generation and above.

[Claim 5]

A method of extracting nucleic acid or protein using dendrimers in accordance with any of claims 1 to 4, wherein protein is extracted using the antigen-antibody reaction by bonding antibodies to the surface of said dendrimers.

[Claim 6]

Dendrimer-compositional substances which are composed of fine particles, multi-layer dendrimers repeatedly synthesized on the surface of these fine particles, and amino radicals covering the surface of the above dendrimers, and are configured so that nucleic acid or protein can be captured by these amino radicals.

[Claim 7]

Dendrimer-compositional substances in accordance with claim 6, wherein said fine particles are those of bacteria-derived magnetic bodies, artificial magnetic bodies, metals, plastic beads, glass beads, or gel state substances.

[Claim 8]

Dendrimer-compositional substances in accordance with claim 6 or claim 7, wherein said dendrimers are laminated on the surface of said fine particles after treating the surface of said fine particles with silane using a sililation reagent or a silane-coupling reagent.

[Claim 9]

Dendrimer-compositional substances in accordance with any of claims 6 to 8, wherein said dendrimers are of the second generation and above.

[Claim 10]

Dendrimer-compositional substances in accordance with any of claims 6 to 9, which are configured so that protein is captured using the antigen-antibody reaction by bonding antibodies to the surface of said dendrimers.

[DETAILED DESCRIPTION OF THE INVENTION]

[0001]

[TECHNICAL FIELD OF THE INVENTION]

The present invention relates to a method of extracting nucleic acid or protein, and more precisely, to a method of extracting nucleic acid or protein by dendrimers using fine particles and dendrimer-compositional substances.

[0002]

[PRIOR ART]

In recent years, automation of DNA extraction has been strongly desired in the fields of medical service and experiments. Commercially-available pre-treatment systems for extracting nucleic acid and protein can be roughly divided into magnetic beads systems (for a magnetic beads system, for example, refer to Non-patent document 1. In addition, these systems are not limited to those using magnetic beads, but also include those using magnetic particles and those using magnetic bodies. For magnetic particles, for example, refer to Patent document 1, and for magnetic bodies, for example, refer to Patent document 2) and centrifugal separation systems.

[0003]

[Non-patent document 1]

DNA Chip utilizing Magnetic Beads" in Section 7 of "DNA Chip Application Technologies," (written by Haruko Takeyama and Tadashi Matsunaga, and supervised by Tadashi Matsunaga, published in July, 2000, by CMC Co. Ltd.).

[Patent document 1]

Gazette of Japanese Laid-open Patent Application No. 8-176212

[Patent document 2]

Gazette of Japanese Laid-open Patent Application 11-313670 [0004]

PROBLEMS TO BE SOLVED BY THE INVENTION

These magnetic beads systems are smaller in size and more easy to handle compared with the centrifugal separation systems.

However, the magnetic beads systems have a problem that they have a rather small rate of capturing nucleic acids or proteins and thus do not necessarily provide satisfactory yields because projected structures for capturing nucleic acids or proteins formed on the surfaces of magnetic beads are sparse.

[0005]

The object of the present invention is to solve the above-described problem, that is, to achieve a nucleic acid or protein-extracting method using dendrimers, which can greatly increase the recovery ratio of nucleic acids or proteins by building dendrimers containing fine particles and covering the dendrimers with amino terminal radicals for capturing nucleic acids or proteins, and to achieve dendrimer-compositional substances.

[0006]

[MEANS FOR SOLVING THE PROBLEMS]

To achieve such an object, the invention disclosed in Claim 1 is characterized in that multi-layer dendrimers are formed on the surface of fine particles, amino radicals are formed on the surface of the dendrimers, and nucleic acid or protein is extracted or recovered using these amino radicals.

When a plurality of generation dendrimers are formed on the surface of the fine particles and amino radicals are formed on the surface of the dendrimers, which holds out capacity to efficiently capture nucleic acid or protein. The present invention is a method of extracting nucleic acid or protein skillfully using this capacity.

[0007]

In this case, for the fine particles, bacteria-derived magnetic bodies, artificial magnetic bodies, metals, plastic beads, glass beads, or gel state substances can be used, as disclosed in Claim 2. Further, the dendrimers are laminated on the surface of the fine particles after

treating the surface of the fine particle with silane using a sililation reagent or a silane-coupling reagent, as disclosed in Claim 3.

Still further, the dendrimers are preferably formed of two-layer or more, as disclosed in Claim 4.

[8000]

Further, as disclosed in Claim 5, protein can be extracted using the antigen-antibody reaction by bonding antibodies to the surface of the dendrimers.

[0009]

The invention disclosed in Claim 6 is characterized in that dendrimer-compositional substances are composed of fine particles, multi-layer dendrimers repeatedly synthesized on the surface of these fine particles, and amino radicals covering the surface of the above dendrimers, and are configured so that nucleic acid or protein can be captured by these amino radicals.

[0010]

In this case, for the fine particles, bacteria-derived magnetic bodies, artificial magnetic bodies, metals, plastic beads, glass beads, or gel state substances can be used, as disclosed in Claim 7. Further, the dendrimers are laminated on the surface of the fine particles after treating the surface of the fine particles with silane using a sililation reagent or a silane-coupling reagent, as disclosed in Claim 8. Still further, the dendrimers are preferably formed of two-layer or more, as disclosed in Claim 9.

More still further, protein can be captured using the antigenantibody reaction by bonding antibodies to the surface of the dendrimers, as disclosed in Claim 10.

[0011]

[EMBODIMENT FOR CARRYING OUT THE INVENTION]

The present invention relates to a method for efficiently

extracting nucleic acid or protein (hereinafter DNA is used as an example) from fluid samples by synthesizing multi-branched modification using polyamide-amine dendrimers on the surface of fine particles, and to dendrimer-compositional substances.

In addition, as fine particles in the present invention, fine particles of bacteria-derived magnetic bodies, artificial magnetic bodies, metals, plastic beads, glass beads, gel-state materials, etc. can be used. However, for this embodiment, the description will refer to a bacteria-derived magnetic body, one of the examples of the fine particle, as an example to simplify the description.

[0012]

The use of a solid-phase magnetic body is a very effective means of extracting DNA from cytoplasmic admixtures. The method of extraction using magnetic bodies can shorten the extracting time, consumes a smaller quantity of reagents used, and is easy to automate the process of separation, when compared with conventional methods. If bacteria-derived magnetic bodies are used as magnetic bodies, each magnetic body consists of a single-phase iron dioxide of size 50 to 60 nm and this is a size suitable for extracting DNA.

[0013]

An embodiment of the present invention will now be described in detail using the drawings. In the present invention, multi-branched polyamide-amine dendrimers are obtained by implementing silanization on the surface of fine particles, such as bio-derived magnetic bodies, using a sililation reagent or a silane-coupling reagent and laminating amide-amine formed by the reaction of methyl acrylate and ethylenediamine on the above silanization as dendrounits.

Fig. 1 is a conceptual configuration drawing for dendrimers formed by such a method.

[0014]

(1) As magnetic body 1, as disclosed in Fig. 1, for instance, a bacteria-derived magnetic body is used. The bacteria-derived magnetic body can be obtained, after breaking bacteria plasma membrane by applying pressure to them, by recovering them using a magnet and applying suitable treatment to them.

[0015]

More specifically, collected bacteria cells are broken in five steps with $1100~{\rm kg/cm^2}$. After applying a uniform magnetic field (the surface magnetic field is $0.37~{\rm T}$) to broken cells, the magnetic bodies are taken out using an Nd-B magnet ($10~{\rm mm}\times 10~{\rm mm}\times 6~{\rm mm}$). Collected magnetic bodies are subjected to disinfection by means of ultrasonic washing three times and then stored in buffer solution at $4^{\circ}{\rm C}$.

[0016]

The magnetic body concentration is determined by the weight in the dry condition. The magnetic bodies are diffused using ultrasonic waves and are dispensed by every 0.5 mL in 5 mL tubes whose weights have been measured after being dried for 4 hours at 180°C in advance. Each of the dispensed magnetic bodies is washed two or more times in an ultrasonic wave chamber using a solution of 1:1:1 concentration of chloroform, methanol, and hexane.

The magnetic bodies are separated from the solution using magnetism to remove solvent. Collected magnetic bodies are dried for four hours at 180°C after removing residual solvent using vacuum drying for 15 minutes.

[0017]

(2) The bacteria-derived magnetic bodies obtained as described above are subjected to silanic modification on their surfaces. The magnetic body solution is dispensed so that a concentration of 100

mg/mL is obtained as a whole, then magnetic bodies are recovered with an Nd-B magnet and the solution is removed. The magnetic bodies are separated using magnetism and the solvent is removed. Collected bacteria-derived magnetic bodies are dried for 15 minutes in vacuum and are suspended in 99% ethanol whose volume is the same as that of the original solution after removing residual solvent.

[0018]

Amino-silane polymers (called AEEA) are subjected to hydrolysis using 1 mM acetic acid 1% solution in 99% ethanol, then directly covalently bonded to the surface of bio-derived magnetic bodies. Further, the magnetic bodies, after being lightly diffused in an ultrasonic wave chamber, are washed with 20 mL methanol three times and again suspended in the solution making them have the same volume as the original one.

[0019]

(3) Next, multi-branched polyamide-amine dendrimers are laminated on the surface of the magnetic bodies subjected to amino-silane treatment as described above.

Dendrimer synthesis is started at the AEEA-coated 50 mg bacteria-derived magnetic bodies (in addition, the synthesis has also been started at the 50 mg artificial magnetic bodies in 20 mL methyl acrylate for the purpose of comparison).

[0020]

In order to disperse the suspended state, an Erlenmeyer flask is dipped in the water in an ultrasonic wave chamber for three hours at 25°C using a completely closed rotary evaporator.

The magnetic bodies are collected and washed with methanol. After washing, they are reacted in the 4 mL methanol and ethylenediamine 1:1 solution and the generated amide-amine is polymerized as a dendro-unit. The synthesis is proceeded while

maintaining the same state thereafter.

[0021]

Polymerization is proceeded by means of repeated reaction of methyl acrylate and ethylenediamine up to a target generation (Fig. 1 shows up to the second layer).

Then, the magnetic bodies are washed three times using 25 mL methanol, and next washed with 25 mL water. In this case, they are collected using magnetism between one washing stage and the next washing stage.

[0022]

(4) Next, the surface amine is determined.

Modified magnetic body 1 (250 μ g) is dipped in 200 μ L 10 mM sulfosuccinimidyl 6 –[3' (2–pyridyldithio)–propioneamide] hexanoate (sulfo-LC-SPDP) solution for 30 minutes and are subjected to growth and extension. Treated magnetic bodies are washed with distilled water three times and are collected using magnetism.

[0023]

The magnetic bodies and sulfo-LC-SPDP polymers are subjected to growth-reaction in 200 μ L 20 mM dithiothreitol, and then also quantitatively measured using a spectroscope at a wavelength of 343 nm. Data are compared with unmodified magnetic bodies for performance and the concentration is determined based on a standard curve obtained using 5 mM sulfo-LC-SPDP and 20 mM dithiothreitol.

[0024]

When the magnetic bodies modified as described above (AEEA 200 μg -modified third-generation dendrimers and AEEA 100 μg -modified fifth- and sixth-generation dendrimers) are mixed with 25 μg of calf thymus DNA, handled to obtain 1 mL in 20 mM trishydrochloric acid buffer solution (Tris-HCl) (pH 7.0), turned upside down, then subjected to a 6000 rpm micro centrifuge, the following

results are obtained:

[0025]

Absorbance of the supernatant liquid is observed at 260 nm and the concentration of DNA is calculated using the standard curve to calf thymus DNA. The DNA can be exfoliated from magnetic bodies by being heavily stirred in 1 mL 2 M NaCl. Existence of DNA can be checked using electrophoresis of agarose gel after implementing ethanol-precipitation.

In addition, the present invention can be applied to extraction of 4.8 kbp pGEM-T plasmid containing luciferase genes.

[0026]

Further, DNA extraction from Escherichia coli and the whole blood for direct PCR analysis has also been tried. Escherichia coli in which luciferase luminous enzyme is inserted into pGEM-T plasmid, are cultured until the cell concentration reaches $10^6/\text{mL}$ in the culture solution containing 50 µg ampicillin. The cells are isolated using centrifugal separation.

[0027]

Cells are dissolved by being dipped in 10% Triton-X solvent containing 75 μg protenase K for 30 minutes at 50°C. Bacteria-derived magnetic bodies grown to the sixth-generation 100 μg are added to the dissolved substances and the tube is quickly stirred. Magnetic bodies are collected using magnetism and the supernatant liquid is removed.

[0028]

The magnetic bodies are washed six times using 20 mM Tris-HCl(pH 7.0) and the tube is shaken vertically every time and suspended substances are collected using magnetism. DNA is stirred sufficiently in 1 mL 2 M NaCl and exfoliated from magnetic bodies. The magnetic bodies are subjected to 6000 rpm centrifugal separation

with a micro centrifuge.

[0029]

DNA Exfoliated is measured with absorption an spectrophotometer and compared with the standard calibration curve A ratio of 260:280 is determined with the for 2 M NaCl. spectrophotometer. On the other hand, for a lot to which the same extraction has been done, DNA is not exfoliated from the magnetic bodies but suspended in 100 µL distilled water (Mill-Q water) without treatment to be used for PCR amplification. This lot is diluted with Mill-Q water while applying ultrasonic waves to the magnetic bodies and plasmid is PCR-amplified.

[0030]

As the forward primer,

5'GGGATGCATATGGAAGACGCCAAAAACATA3'

is used, and as the backward primer,

5'GGGATGCATACTTGATTACAATTTGGACTTTCC3'

is used. In such a condition, 1.65 kbp luciferase genes found in plasmid are amplified.

[0031]

The PCR products can be visualized by gel electrophoresis. DNA extracted from 1 μ L human whole blood is also analyzed following the similar procedure using PCR. New samples are used and the anti-coagulative agent is not used.

[0032]

As the forward primer used for PCR in the whole blood, 5'GGCCTCCCACACCAG3'

is used, while as the backward primer,

5'GCGGGCAGCGTCAGCACCAGTA3'

is used.

[0033]

The above-described points are summarized below.

The number of amines on the surface of the bacteria-derived magnetic bodies increases as the number of dendrimer layers increases from 1 to 6. As shown in Fig. 1, it is theoretically shown that the number of amines is doubled every time the number of generations increases from the start-line amino-silane layer.

[0034]

Table 1 indicates the number of amines of bacteria-derived magnetic bodies (BMP) in each generation. As shown in Table 1, the fact that amines double in number in each layer means that dendrimers maintain an ideal cascade construction. The surface area of one bacteria-derived magnetic body, if it is assumed to be a rectangular solid of $50 \times 50 \times 100$ (nm), is 2.5×10^4 nm². On the surface of the sixth-generation layer, since the number of amines is 1.7×10^6 , the numeric value of 68 amines/nm² is obtained.

[0035]

Table 1

Generation	Number amines/BMP	of Ratio of increase
AEEA	2.1×10^{4}	
First generation	6.8×10^{4}	350
Third generation	2.6×10^{5}	370
Fifth generation	1.1×10^{6}	420
Sixth generation	1.7×10^{6}	150

[0036]

Fig. 2 shows photographs for modified and unmodified bacteriaderived magnetic bodies taken with an electron microscope. As shown in Fig. 2 (a), unmodified magnetic bodies have mutual weak repulsive forces and it can be seen that they coagulate. Dendrimers of the third generation run in a chaining manner as shown in Fig. 2 (b) and coagulate partly. Dendrimers of the sixth generation are obviously dispersed as seen in Fig. 2 (c). And as shown in Fig. 2 (d), a layer of about 4 nm covering the surface of the magnetic bodies is observed.

[0037]

Extreme deterioration is not recognized for dendrimer-modified bacteria-derived magnetic bodies even after ultrasonic waves are applied. They are very well diffused without making large coagulation and, even if ultrasonic waves are not applied, they are sufficiently well diffused and suspended.

[0038]

On the other hand, for artificial magnetic bodies, it is confirmed that they become easy to crush gradually as the number of generations increases when ultrasonic waves are applied. Table 2 shows the sizes and distribution of formed magnetic bodies.

If artificial magnetic bodies are dendrimer-extended up to the sixth generation, a large amount of about 14 nm fragments is diffused in the solution. Further, owing to the size being decreased and the structure becoming incomplete, coagulation is greatly decreased and paramagnetic fragments are generated.

[0039]

Table 2

		Distribution (%)	Distribution (%)	Distribution (%)
		(> 125 nm)	(50 - 125 nm)	(< 50 nm)
Bacteria bodies Without coveri	magnetic ing	6	94	0
Bacteria bodies The sixth gene	magnetic eration	1	99	0

Artificial	magnetic	18	82	0
bodies				
Unmodified				
Artificial	magnetic	0	34	66
bodies				
First generat	ion			
Artificial	magnetic	0	17	82
bodies				
Third genera	tion			
Artificial	magnetic	0	0	100
bodies				
Sixth generat	tion			

[0040]

If dendrimers are continually grown on bacteria-derived magnetic bodies, it is found that the magnetic bodies are capable of capturing DNA efficiently as shown in Table 3. In this case, modified magnetic bodies are mixed with 25 μg calf thymus DNA. Magnetic bodies on which dendrimers are extended up to the sixth generation are mixed with excess concentration DNA (50 μg).

[0041]

Table 3

Generation	DNA per 100 μg of magnetic bodies	
	(μg)	
AEEA	3.59 ± 0.37	
First generation	4.43 ± 0.26	
Third generation	5.89 ± 0.07	
Fifth generation	11.95 ± 0.68	
Sixth generation	24.83 ± 1.61	

[0042]

The amount of capturing DNA increases as the dendrimer layer increases at dendrimer-modified magnetic bodies and in the sixth generation, 24.83 \pm 1.61 μg of DNA can be captured per 100 μg of magnetic bodies.

[0043]

For the artificial magnetic bodies, the amount recovered by the AEEA layer shows no change with the amount of DNA captured by the dendrimer-extended layer. This is considered to be due to deterioration such as cracks, crushing, etc. in the magnetic bodies caused by ultrasonic waves.

[0044]

At bacteria-derived magnetic bodies which are dendrimer-modified up to the sixth generation, DNA recovery is not sufficient if only 2 M NaCl is added resulting in only 24% recovery (refer to Table 4). The recovery ratio increases up to 87% (21.7 \pm 1.59 μ g) by maintaining DNA polymers for 30 minutes at 50°C in a thermostatic oven to increase the recovery ratio.

[0045]

Table 4

DNA	Conditions	DNA (μg)/100 μg	Recovery ratio
Calf thymus	30°C, 10 min.	6.07 ± 1.01	24%
Plasmid	50°C, 30 min.	21.70 ± 1.59	87%
Plasmid digests	50°C, 30 min.	19.22 ± 1.61	81%

[0046]

The capturing capability of small plasmid DNA is also investigated. Two kinds of products of about 3 kbp and 1.6 kbp are formed by extracting plasmid pGEM-T containing luciferase genes. The amounts of capture and recovery of plasmid DNA are 23.80 ± 3.01 µg and 19.22 ± 1.61 µg respectively. After examining these results using gel electrophoresis, no discrepancy based on the difference of sizes is recognized. As shown in Fig. 3 (a), recovered DNA corresponds with the DNA recovered using magnetism in advance.

[0047]

The amount of DNA extracted from Escherichia coli is measured

after it is recovered by exfoliation from the magnetic bodies using 2 M NaCl. As a result of measurement of recovered DNA after treatment with ribonuclease (RNase), $30.25 \pm 7.74 \,\mu g$ of DNA was recovered per $100 \,\mu g$ of the sixth generation dendrimer-modified magnetic bodies.

The ratio of 260:280 (nm) is 0.93, showing that mixing of some protein occurs. The result of the previously-mentioned gel electrophoresis also shows that some degree of RNA contamination occurs.

[0048]

As the result, after cytolysis, 3 μ L RNase was added and when the DNA was measured after incubation for 20 minutes at 37°C, the recovery ratio of DNA decreased to 22.35 \pm 1.76 μ g. PCR was implemented for the sample at a dilution ratio of 10 to 100-fold directly without lysis treatment of composite substance composed of magnetic bodies and DNA using a salt or RNase [refer to Fig. 3 (b)].

In a similar manner, for DNA extracted from human whole blood, PCR could be directly implemented at a dilution ratio of 10 to 100-fold by the same process.

[0049]

Based on the above results, the following conclusions can be obtained:

It is widely known that dendrimer modification can be extended in a stratified manner by the fact that amino-silane makes covalent bonding to bacteria-derived magnetic bodies as a polymerization initiator, and that stable cross-linking can be formed on bacteriaderived magnetic bodies obtained from magnetic bacteria AMB-1 using the conjugated bonding of amino-silane.

[0050]

It is sufficient to examine the number of amine radicals on the surface of magnetic bodies for judging whether dendrimers are successfully formed on the bacteria-derived magnetic bodies. It is recognized that the number of amine radicals on the surface is linearly doubled in every generation up to the sixth generation. However, after the sixth generation, the number of amine radicals could not be accurately counted.

[0051]

This is because large cyclic sulfo-LC-SPDP hexamer seems to cause steric-hindrance. In addition, it has been known previously that, as the generation increases, the time required for incubation must be taken longer following the increase.

[0052]

That is, it has been considered that molecules must be grown by allowing sufficient time to avoid steric hindrance in the growth of molecules. In order to extend to the sixth generation from the fifth generation, the incubation time has to be extended up to six hours until it is acknowledged that amine radicals do not increase further even if reagents are added more.

[0053]

Accordingly, although further repetition of generation may be possible over the sixth generation, it cannot be easily determined physically. In addition, deducing from TEM (transmission electron microscope) images, the inter-ion repulsive force increases as the generation increases. Bacteria-derived magnetic bodies coagulate tightly only in the first generation. If there are generations up to the third generation, bacteria-derived magnetic bodies run like a row in a chaining manner. This phenomenon is also suggested by the fact that the strength of magnetic forces is proportional to the magnetic flux density in the direction of magnetic poles as shown in Fig. 4.

[0054]

The existence of ion repulsive force tends to suppress the polar

alignment of magnetic bodies. This is the same in the case where bacteria-derived magnetic bodies are covered with bio-membrane. That is, the repulsive force of the sixth-generation dendrimers is very large, exceeds the magnetic force and thus the magnetic bodies do not coagulate but are actually individually suspended.

[0055]

Although synthesis of magnetic bodies artificially is possible, their dynamic characteristics and chemical behavior as physical properties are not definite because their shapes are not equal, crystallization is not sufficient, and their structure is not uniform. If dendrimers of the same size as bacteria-derived magnetic bodies are formed using artificial magnetic bodies, the artificial magnetic body polymers may cause coagulation and crushing and the increase of amine radicals on the surface may not become linear.

Since bio-derived magnetic bodies are crystallized, they do not suffer a loss even in the dendrimer forming process and maintain the original shapes and magnetism.

[0056]

The dendrimer-modified bio-derived magnetic bodies greatly increase the recovery ratio of DNA compared with unmodified magnetic bodies. DNA is condensed in a regular structure of strong silane cations covering the surface of magnetic bodies and becomes a similar form to dendrimers through interactions with dendrimers. Positive ions, which are increased due to dendrimer-modified bio-derived magnetic bodies, greatly serve to increase the force to capture DNA which is charged negatively. This is also known by the fact that the addition of positive ion reagent increases DNA concentration.

[0057]

However, the addition of positive ion reagent may cause unnecessary contamination. If dendrimer-modified bio-derived

magnetic bodies are used, the DNA recovery ratio can be raised without adding positive ion reagent. Further, as is well known, the degree of dispersion and composite concentration in solution can be controlled by adjusting the number of amino radicals on the surface.

[0058]

The use of magnetic bodies as seen in the present invention is superior to conventional methods in respect of treatment time, amount of reagent to be used, separation and recovery, and ease of automation. The process is very simple, only requiring a dissolving process before the washing process. In addition, if there is a limitation that PCR must be performed from a small amount of sample, this is the most suitable method for extracting sufficient DNA from a small amount of sample. This method is also applicable to designing a more compact system.

[0059]

Furthermore, the present invention is not restricted to the above embodiment but may be embodied in other specific forms, changes, and versions without departing from the spirit or essential characteristics thereof.

[0060]

For example, it is also possible to bond antibodies to the dendrimer surfaces and extract proteins using the antigen-antibody reaction.

[0061]

[EFFECT OF THE INVENTION]

As described above, the present invention has the following effects:

(1) By multi-branching dendrimers on the surface of bio-derived fine particles and covering them with amino terminal radicals, the ratio of extraction of nucleic acids or proteins can be easily increased.

(2) The use of dendrimers containing fine particles is superior to conventional methods of using magnetic beads in respect of treatment time, amount of reagent to be used, separation and recovery, and ease of automation.

[0062]

(3) Although strong ultrasonic waves must be applied to dendrimers for sufficient diffusion, when the surface of fine particles is to be dendrimer-modified, to prevent coagulation, if bio-derived magnetic bodies are used as fine particles, sufficient dendrimers can be formed easily without causing cracking due to ultrasonic waves.

[BRIEF DESCRIPTION OF THE DRAWINGS]

[Fig. 1]

A conceptual configuration drawing for dendrimers in the present invention.

[Fig. 2]

Electron-microscope photographs of bacteria-derived magnetic bodies.

[Fig. 3]

A drawing indicating the results of electrophoresis for DNA.


[Fig. 4]

A drawing illustrating the magnetic field of a bacteria-derived magnetic body.


[Reference of Numerals]

1 magnetic body







Best Available Copy



[Fig. 3]





Best Available Copy



[NAME OF DOCUMENT]

ABSTRACT

[SUMMARY]

[PURPOSE] There are achieved a method of extracting nucleic acid or protein using dendrimers, which can greatly increase the recovery ratio of nucleic acids or proteins by building dendrimers containing fine particles and covering the dendrimers with amino terminal radicals for capturing nucleic acids or proteins, and dendrimer-compositional substances.

[CONSTITUTION] Multi-layer dendrimers are formed on the surface of fine particles, amino radicals are formed on the surface of the dendrimers, and nucleic acid or protein is extracted using these amino radicals.

[SELECTED DRAWINGS]

Fig. 1